



EWB[®] – ER 308L MIG / TIG Welding Wires

Classifications:

EN ISO 14343-A:2007 : W 19 9 L
EN ISO 14343-B:2007 : SS 308L
AWS A5.9: ER308L

Material No. 1.4316

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si
<0.03	19.50 - 22.00	9.00 - 11.00	1.00 - 2.50	0.30 - 0.65

Description:

- MIG / TIG welding of 18%Cr-8%Ni austenite stainless steels (AISI STS 301, 302, 304)

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 320	min. 520	min. 35

Welding Parameters:

Wire Diameter (Ø in mm)	0.80	1.00	1.20
Pulsed Arc (A)	100 - 150	120 - 200	140 - 220
Voltage (V)	22 - 27	24 - 28	24 - 28

Packing Available:-

MIG/MAG Wire (Ø in mm): 0.80 / 1.00 / 1.20

TIG Wire (Ø in mm): 1.60 / 2.40 / 3.20 / 4.00

EWB Weld

A-112, DDA Sheds Okhla Industrial Area,
Phase-II, NEW DELHI – 110 020

e-mail: info@ewbweld.com web: www.ewbweld.com

An ISO 9001:2015 Quality Management System Certified Co.