



EWB[®] – ER 309LMo MIG / TIG Welding Wires

Classifications:

EN ISO 14343-A:2007 : W 23 12 2 L
AWS A5.9: ER309LMo

Material No. ~1.4459

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mo	Mn	Si
<0.03	23.00 – 25.00	12.00 – 14.00	2.00 – 3.00	1.00 - 2.50	0.30 – 0.65

Description:

- MIG / TIG welding of 22%Cr-12%Ni-2%Mo austenite stainless steels.

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 350	min. 550	min. 25

Welding Parameters:

Wire Diameter (Ø in mm)	0.80	1.00	1.20
Pulsed Arc (A)	100 - 150	120 - 200	140 - 220
Voltage (V)	22 - 27	24 - 28	24 - 28

Packing Available:-

MIG/MAG Wire (Ø in mm): 0.80 / 1.00 / 1.20

TIG Wire (Ø in mm): 1.60 / 2.40 / 3.20 / 4.00

EWB Weld

A-112, DDA Sheds Okhla Industrial Area,
Phase-II, NEW DELHI – 110 020

e-mail: info@ewbweld.com web: www.ewbweld.com

An ISO 9001:2015 Quality Management System Certified Co.